

项 目Item	质量指标Quality Index								试验方法 Test Method
	IR60		IR70		IR80		IR90		
	优等品 Premi- um grade	合格品 On_ spec grade	优等品 Premi- um grade	合格品 On_ spec grade	优等品 Premi- um grade	合格品 On_ spec grade	优等品 Premi- um grade	合格品 On_ spec grade	
生胶门尼黏度 ML ( 1+4 ) 100°C Mooney viscosity of raw rubber	55-64		65-74		75-84		85-95		GB/T 1232.1
挥发分质量分数/% mass fraction of volatile ≤	0.6	0.8	0.6	0.8	0.6	0.8	0.6	0.8	GB/T 6737
灰分质量分数/% mass fraction of ash ≤	0.50								GB/T 4498
300%定伸应力/MPa tear strength at 300%	报告Report								GB/T 528
拉伸强度 ( 40min ) a/MPa Tensile strength ≥	25.0		26.0						GB/T 528
拉断伸长率 ( 40min ) a/% Tensile elongation ≥	450		460						GB/T 528
注：( 1 ) 采用标准参比炭黑3# ( SBR3# ) 进行评价 using reference carbon black for evaluation									